



Product Change Notification

ENP-PCN-2010-01 Rev 01
June 28, 2010

PCN Overview

PCN Original Issue Date:	April 12, 2010	
Type of Change Notification:	Assembly material & site change	
Qualification Complete:	June 15, 2010	
Sample Availability:	June 15, 2010	
Expected First Ship Date:	August 15, 2010	
Last Date to Buy Pre-Change Product:	N/A	
Affected Products:	EN5322QI, EA102BCM, EN103INT, EN106AMN	
Reference Documents:	JEDEC Standard JESD46C Prod Mark Spec OP-L01a_V9-02.pdf	
PCN Revision History:		
Revision Date: April 12, 2010	Revision Number: 00	Reason: initial issue
Revision Date: June 28, 2010	Revision Number: 01	Reason: qualification complete

Description of Change

Enpirion has qualified copper bond material for QFN devices at HANA Semiconductor, Thailand.

Enpirion reserves the right to ship devices with either gold or copper wire bonds.

Customer Impact of Change and Recommended Action

There is no customer impact since there is no change in form, fit, function, reliability and quality of the products.

Reason for Change

Copper wire is increasingly becoming the material of choice for wire bonding in the semiconductor industry due to the spiraling cost of gold. Addition of copper wire as a qualified material for assembly is an integral part of Enpirion's cost containment strategy while enabling manufacturing flexibility and ensuring long term continuity of supply.

Product Identification

Products with copper wire will be easily identifiable by the letter C at the end of the Lot Number on the second row of the device marking.

Copper Wire

o EN5322QI
XXXXXC
XYWWW

Gold Wire

o EN5322QI
XXXXX
XYWWW

Product Qualification Data

Devices manufactured with copper wire bonds at HANA Semiconductor, Thailand

Item	Reliability Test	Test Condition & Standard	Test Results (Qty: Pass/Fail)		
			Lot #1	Lot #2	Lot #3
1	High Temperature Operating Life (HTOL)	JESD22-A108 (125°C, Vin-max, 1000 hours)	26/0	26/0	26/0
2	High Temperature Storage (HTS)	JESD22-A-103-C (150°C, 1000 hours, Condition B)	80/0	80/0	80/0
3	Pre-Conditioning	JESD22-A-113 and J-STD-020	200/0	160/0	160/0
4	Temperature Humidity Bias with Pre-Conditioned Devices from Item 3	JESD22-A101 (85°C/85%RH, Vin-max, 500 hours)	40/0	—	—
5	Autoclave with Pre-Conditioned Devices from Item 3	JESD22-A102C (100%RH, 121°C, 96 hours, Condition C)	80/0	80/0	80/0
6	Temperature Cycle with Pre-Conditioned Devices from Item 3	-65°C to +150°C / 500 cycles JESD22-A104, Condition C, Soak Mode 5	80/0	80/0	80/0

Product characterization data and product samples are available on request.

Customer Acknowledgement

Customers are requested to acknowledge this notification within 30 days of its issue date. Lack of response within 30 days of PCN release will constitute an acceptance of the change.

Please contact Enpirion at customerservice@enpirion.com, your manufacturers' representative, or distributor if you have any issues with this PCN or require additional information.

Customer: _____ Name: _____
 Title: _____ Phone: _____ Email: _____
 Customer Comments: _____
 Customer Signature: _____ Date: _____

Contact Information

Enpirion Headquarters:
 Enpirion, Inc.
 Perryville III
 53 Frontage Road, Suite 210
 Hampton, NJ 08827

Phone: 908 894 6000 Fax: 908 894 6090
 Customer Service: 408 904 2801 Email: customerservice@enpirion.com

To locate your area Representative or Distributor visit the Enpirion Website: www.enpirion.com

This document does not grant any license, express or implied, by estoppels or otherwise, to any Enpirion intellectual property. Except as provided in the specific terms and conditions of sale, Enpirion does not provide any warranty, either express or implied, relating to the sale or use of Enpirion products for any particular purpose, merchantability, or relating to infringement of any patent, copyright, or other intellectual property right. Enpirion products are not intended for use in medical, life saving, or life sustaining applications. Enpirion reserves the right to make changes to specifications and product descriptions at any time, without notice.